

AXIOTHERM® PCMs are designed to absorb and release large quantities of thermal energy at constant temperatures. Over 30 organic (ATP) and inorganic (ATS) high-performance PCM in a temperature range between -40 °C to 140 ° are available in special macro-encapsulated form with an optimized surface-to-mass ratio for faster energy exchange and improved performance in practical applications. Standardised solutions such as our HeatSel®s and HeatPlates are available for water and air-based applications and can be adapted to your specific requirements.


Key features of the AXIOTHERM® PCM are:

- High heat storage capacities
- Consistent, repeatable performance over thousands of thermal cycles
- Simple and safe handling
- Also based on renewable raw materials, nontoxic and biodegradable



Typical Values

Melting temperature	°C	27 to 29
Congeeing temperature	°C	26 to 28
Heat storage capacity* temperature range of 20 – 35°C	kJ/kg	265
Specific heat capacity	kJ/kg*K	2
Density (liquid)	kg/l	0,76
Heat conductivity	W/(m*K)	0,2
Volume expansion	%	>10
Max. operating temperature	°C	70
Flash point	°C	>180



Axiotherm GmbH
 Bahnhofstraße 31
 D-07607 Eisenberg/Thüringen
 Phone: +49 (0) 36691 53 118
 Fax: +49 (0) 36691 53 120
 E-Mail: Mailbox@axiotherm.de
 Web: www.axiotherm.de

The product information given is a non-binding planning aid, subject to technical changes without notice.
 Version: 31.01.2018

*Measured with 3-Layer-Calorimeter